

Nominal $D_p$ (nm)	Actual $D_p$ (nm)	$D_{me}$ (nm)	Mass (fg)	$\rho_{eff}$ ( $\text{g cm}^{-3}$ )	$\chi^*$ without internal voids	$\chi$ with internal voids	$F_{vs}$ (%)	$d_{pp}$ (nm)	$N$
75	$76.0 \pm 1.4$	$57.1 \pm 0.2$	$0.17 \pm 0.01$	$0.77 \pm 0.08$	$1.66 \pm 0.03$	1.04	58	27.9	8
100	$99.0 \pm 1.1$	$70.8 \pm 1.2$	$0.33 \pm 0.02$	$0.65 \pm 0.07$	$1.81 \pm 0.04$	1.03	63	28.5	15
150	$146.2 \pm 1.4$	$95.3 \pm 1.1$	$0.77 \pm 0.03$	$0.48 \pm 0.04$	$2.10 \pm 0.03$	1.04	72	27.7	39
200	$193.3 \pm 3.4$	$116.2 \pm 4.2$	$1.46 \pm 0.16$	$0.39 \pm 0.09$	$2.29 \pm 0.09$	1.08	78	28.0	72